

### AMENDMENTS TO THE CLAIMS


1. (Currently amended) An optical disk comprising a first substrate, a first reflective layer for reflecting laser beams for information reading formed on the first substrate, and a resin layer made of a cured film of an ultraviolet curable composition formed on the first reflective layer, wherein

the first reflective layer is a reflective layer made of silver or an alloy containing silver as a main component, and


the ultraviolet curable composition contains:

(a) a radical polymerizable compound,


(b) a compound represented by the formula [(1)]\_(3):



wherein R<sup>7</sup> represents an alkyl group having 1 to 20 carbon atoms which may be substituted with a hydrogen atom or a halogen atom, or an alkenyl group having 1 to 20 carbon atoms which may be substituted with a halogen atom



wherein R<sup>1</sup>, R<sup>2</sup>, R<sup>3</sup>, R<sup>4</sup> and R<sup>5</sup> each independently represents (i) a hydrogen atom, (ii) a halogen atom, (iii) a hydroxyl group, (iv) an alkoxyl group having 1 to 8 carbon atoms, (v) a carboxyl group, (vi) a group represented by the formula (2):



(wherein R<sup>6</sup> represents an alkyl group having 1 to 20 carbon atoms which may be substituted with a halogen atom, or an alkenyl group having 1 to 20 carbon atoms which may be substituted with a halogen atom), or (vii) an alkyl or alkenyl group having 1 to 24 carbon atoms which may

~~have a carboxyl group, an alkoxycarbonyl group, an acyloxy group or an alkoxy group as a substituent, and at least one of R<sup>1</sup>, R<sup>2</sup>, R<sup>3</sup>, R<sup>4</sup> and R<sup>5</sup> is a hydroxyl group, and (c) a radical photopolymerization initiator, and~~  
(c) a radical photopolymerization initiator.

2. (Original) The optical disk according to claim 1, wherein a second substrate comprising a second reflective layer for reflecting laser beams for information reading formed thereon is formed on the resin layer so as to contact the resin layer with the second reflective layer.

Claims 3-13: Canceled

14. (Previously presented) The optical disk according to claim 2, wherein the content of the compound represented by the formula (1) is from 0.05 to 10% by mass based on the total amounts of the ultraviolet curable composition.


Claims 15-24: Canceled

25. (Previously presented) The optical disk according to claim 1, wherein the content of the compound represented by the formula (1) is from 0.05 to 10% by mass based on the total amounts of the ultraviolet curable composition.

26. (New) An optical disk comprising a first substrate, a first reflective layer for reflecting laser beams for information reading formed on the first substrate, and a resin layer made of a cured film of an ultraviolet curable composition formed on the first reflective layer, wherein the first reflective layer is a reflective layer made of silver or an alloy containing silver as a main component, and

the ultraviolet curable composition contains:

- (a) a radical polymerizable compound,
- (b) a compound represented by the formula (6):



wherein  $R^{19}$ ,  $R^{20}$ ,  $R^{21}$  and  $R^{22}$  each independently represents a hydrogen atom, a halogen atom, alkoxyl group having 1 to 8 carbon atoms, an alkyl group having 1 to 24 carbon atoms which may have  $-COOH$ ,  $-COOR^{12}$ ,  $-OCOR^{13}$  or  $-OR^{14}$  as a substituent, or an alkenyl group having 1 to 24 carbon atoms which may have  $-COOH$ ,  $-COOR^{12}$ ,  $-OCOR^{13}$  or  $-OR^{14}$  as a substituent (wherein  $R^{12}$ ,  $R^{13}$  and  $R^{14}$  each independently represents an alkyl group having 1 to 8 carbon atoms or an alkenyl group having 1 to 8 carbon atoms), and  
(c) a radical photopolymerization initiator.

27. (New) An optical disk comprising a first substrate, a first reflective layer for reflecting laser beams for information reading formed on the first substrate, and a resin layer made of a cured film of an ultraviolet curable composition formed on the first reflective layer, wherein  
the first reflective layer is a reflective layer made of silver or an alloy containing silver as a main component, and

the ultraviolet curable composition contains:

- (a) a radical polymerizable compound,
- (b) a compound which is at least one selected from the group consisting of gallic acid, 2-hydroxyhydroquinone and resorcinol, and
- (c) a radical photopolymerization initiator.